

## AMPRIME CEM-2000

Made with selected binders, additives and aggregates AMPRIME CEM-2000 is a non- shrink expansion flow grout can be used both as adhesive and grout.

Fractures:

- Good bond to concrete
- Non-Corrosive
- Non-Scramble and Non-Toxic
- Early strength gain
- Easy to mix and ease of application
- Vibration resistance

Direction for use:

Mix 25Kgs CEM-2000 with 3.700 – 3.800 litters of water. First Pour the entire water and pour CEM-2000 slowly with regular mixing until complete free flow grout.

Substrate must be completely dirt free.

Surface must be wetted with water prior application

Surface temperature must range between 5.45 degree Celsius during application

Curing:

Curing can be done by wet hessian or curing agents

At cold temperature area warm water is advisable for curing. Cold water can be used for warm weather area

Thickness & limited

CEM-2000 can be applied be single layer at 10-100 MM